

Contract no: 20894A4/3/018

Continuum Mechanics of Materials

V. A. Lubarda

Department of Mechanical and Aerospace Engineering,

University of California, San Diego, La Jolla, CA 92093-0411, USA

The concept of yield surface and plastic loading/unloading criteria in stress and strain space are discussed in Section 1. Plasticity postulates of Ilyushin and Drucker, and their implications on plastic normality rules and convexity of the yield surface are described in Section 2. General constitutive framework of rate-independent isothermal plasticity at finite strain is presented in Section 3. Stress and strain space formulations are given for the smooth yield surface and for the yield surface with a vertex. Particular constitutive models for plastic deformation of metals are considered in Section 4. These include models of isotropic, kinematic, and combined hardening, as well as multi-surface hardening models. Section 5 deals with pressure-dependent plasticity. Drucker-Prager yield condition for geomaterials, and Gurson yield condition for porous metals are introduced, and the corresponding constitutive equations are derived. Non-associative plasticity, in which plastic strain rate is normal to the plastic potential surface, distinct from the yield surface, is presented in

Section 6. A yield vertex model for fissured rocks is then described. Section 7 contains fundamentals of deformation theory of plasticity and its relationship to more general flow theory of plasticity. Applicability of deformation theory for proportional and nearly proportional loading is discussed. Constitutive equations of non-isothermal plastic deformation are considered in Section 8. Specific results are listed for non-isothermal isotropic and kinematic hardening idealizations. Section 9 deals with essential structure of the rate-dependent plasticity. Flow potential representations are given for the power-law and for the Johnson-Cook models of the rate-dependent plasticity, and for viscoplastic model of Malvern and Perzyna. Bibliography contains selected references cited in the article.

1 Yield Surface

Materials capable of plastic deformation usually have an elastic range of purely elastic response. This range is a closed domain in either stress or strain space whose boundary is called the yield surface. The shape of the yield surface depends on the entire deformation path from the reference state. The yield surfaces for actual materials are mainly smooth, but may have or develop pointed pyramidal or conical vertices. Physical theories of plasticity (Hill, 1967) imply the formation of a corner or vertex at the loading point on the yield surface. Experimental evidence, on the other hand, suggests that, while relatively high curvature at the loading point is often observed, sharp corners

are seldom seen (Hecker, 1976). Experiments also indicate that yield surfaces for metals are convex in Cauchy stress space, if elastic response within the yield surface is linear and unaffected by plastic flow.

1.1 Yield Surface in Strain Space

The yield surface in strain space is defined by $g(\mathbf{E}, \mathcal{H}) = 0$, where \mathbf{E} is the strain tensor, and \mathcal{H} the pattern of internal rearrangements due to plastic flow, i.e., the set of appropriate internal variables including the path history by which they are achieved (Rice, 1971). The shape of the yield surface specified by function g is different for different choices of \mathbf{E} . If elastic response within the yield surface is Green-elastic, associated with the strain energy $\psi = \psi(\mathbf{E}, \mathcal{H})$ per unit reference volume, the corresponding stress is $\mathbf{T} = \partial\psi/\partial\mathbf{E}$. From the strain state on the current yield surface, an increment of strain $d\mathbf{E}$ directed inside the yield surface constitutes an elastic unloading. The associated incremental elastic response is governed by

$$\dot{\mathbf{T}} = \mathbf{\Lambda} : \dot{\mathbf{E}}, \quad \mathbf{\Lambda} = \frac{\partial^2 \psi}{\partial \mathbf{E} \otimes \partial \mathbf{E}}, \quad (1)$$

where $\mathbf{\Lambda} = \mathbf{\Lambda}(\mathbf{E}, \mathcal{H})$ is a tensor of elastic moduli of the material at the considered state of strain and internal structure. An increment of strain directed outside the current yield surface constitutes plastic loading. The resulting increment of stress consists of elastic and plastic parts, such that

$$\dot{\mathbf{T}} = \dot{\mathbf{T}}^e + \dot{\mathbf{T}}^p = \mathbf{\Lambda} : \dot{\mathbf{E}} + \dot{\mathbf{T}}^p. \quad (2)$$

The elastic part of the stress rate $\dot{\mathbf{T}}^e$ gives a stress decrement $d^e\mathbf{T}$ associated with elastic removal of the strain increment $d\mathbf{E}$. The plastic part of the stress rate $\dot{\mathbf{T}}^p$ gives a residual stress decrement $d^p\mathbf{T}$ in a considered infinitesimal strain cycle. A transition between elastic unloading and plastic loading is a neutral loading, in which an infinitesimal strain increment is tangential to the yield surface and represents pure elastic deformation. Thus,

$$\frac{\partial g}{\partial \mathbf{E}} : \dot{\mathbf{E}} \begin{cases} > 0, & \text{for plastic loading,} \\ = 0, & \text{for neutral loading,} \\ < 0, & \text{for elastic unloading.} \end{cases} \quad (3)$$

The gradient $\partial g/\partial \mathbf{E}$ is codirectional with the outward normal to a locally smooth yield surface $g = 0$ at the state of strain \mathbf{E} . For incrementally linear response, all infinitesimal increments $d\mathbf{E}$ with equal projections on the normal $\partial g/\partial \mathbf{E}$, produce equal plastic increments of stress $d^p\mathbf{T}$, since the components of $d\mathbf{E}$ obtained by projection on the plane tangential to the yield surface represent elastic deformation only.

1.2 Yield Surface in Stress Space

The yield surface in stress space is defined by $f(\mathbf{T}, \mathcal{H}) = 0$. The stress \mathbf{T} is a work-conjugate to strain \mathbf{E} , in the sense that $\mathbf{T} : \dot{\mathbf{E}}$ represents the rate of work per unit initial volume (Hill, 1978). The function f is related to g by

$$f[\mathbf{T}(\mathbf{E}, \mathcal{H}), \mathcal{H}] = g(\mathbf{E}, \mathcal{H}) = 0, \quad (4)$$

provided that physically identical conditions of yield are imposed in both spaces. If elastic response within the yield surface is Green-elastic, associated with the complementary strain energy $\phi = \phi(\mathbf{T}, \mathcal{H})$ per unit reference volume, the corresponding strain is $\mathbf{E} = \partial\phi/\partial\mathbf{T}$. For material in the hardening range relative to measures \mathbf{E} and \mathbf{T} , an increment of stress $d\mathbf{T}$ from the stress state on the yield surface, directed inside the yield surface constitutes an elastic unloading. The associated incremental elastic response is governed by

$$\dot{\mathbf{E}} = \mathbf{M} : \dot{\mathbf{T}}, \quad \mathbf{M} = \frac{\partial^2 \phi}{\partial \mathbf{T} \otimes \partial \mathbf{T}}. \quad (5)$$

The tensor $\mathbf{M} = \mathbf{M}(\mathbf{T}, \mathcal{H})$ is a tensor of elastic compliances of the material at the considered state of stress and internal structure. An increment of stress directed outside the current yield surface constitutes plastic loading in the hardening range of material response. The resulting increment of strain consists of elastic and plastic parts, such that

$$\dot{\mathbf{E}} = \dot{\mathbf{E}}^e + \dot{\mathbf{E}}^p = \mathbf{M} : \dot{\mathbf{T}} + \dot{\mathbf{E}}^p. \quad (6)$$

During plastic loading of hardening material, the yield surface locally expands, the stress state remaining on the yield surface. The elastic part of the strain rate $\dot{\mathbf{E}}^e$ gives an elastic increment of strain $d^e\mathbf{E}$ which is recovered upon elastic unloading of the stress increment $d\mathbf{T}$. The plastic part of the strain rate $\dot{\mathbf{E}}^p$ gives a residual increment of strain $d^p\mathbf{E}$ which is left upon removal of the stress increment $d\mathbf{T}$. A transition between elastic unloading and plastic loading is a neutral loading, in which an infinitesimal stress increment is tangential to the

yield surface and produces only elastic deformation. Thus, in the hardening range

$$\frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} \begin{cases} > 0, & \text{for plastic loading,} \\ = 0, & \text{for neutral loading,} \\ < 0, & \text{for elastic unloading.} \end{cases} \quad (7)$$

The gradient $\partial f/\partial \mathbf{T}$ is codirectional with the outward normal to a locally smooth yield surface $f = 0$ at the state of stress \mathbf{T} . For incrementally linear response, all infinitesimal increments $d\mathbf{T}$ with equal projections on $\partial f/\partial \mathbf{T}$ produce equal plastic increments of deformation $d^p \mathbf{E}$, since the components of $d\mathbf{T}$ obtained by projection on the plane tangential to the yield surface give rise to elastic deformation only.

In a softening range of material response Eq. (6) still holds, although the elastic and plastic parts of the strain rate have purely formal significance, since in the softening range it is not physically possible to perform an infinitesimal cycle of stress starting from a stress point on the yield surface. The hardening is, however, a relative term: material that is in the hardening range relative to one pair of stress and strain measures, may be in the softening range relative to another pair.

2 *Plasticity Postulates, Normality and Convexity of the Yield Surface*

Several postulates in the form of constitutive inequalities have been proposed for certain types of materials undergoing plastic deformation. The two most

well-known are by Drucker (1960) and Ilyushin (1961).

2.1 Ilyushin's Postulate

According to Ilyushin's postulate the net work in an isothermal cycle of strain must be positive

$$\oint_E \mathbf{T} : d\mathbf{E} > 0, \quad (8)$$

if a cycle at some stage involves plastic deformation. The integral in (8) over an elastic strain cycle is equal to zero. Since a cycle of strain that includes plastic deformation in general does not return the material to its state at the beginning of the cycle, the inequality (8) is not a law of thermodynamics. For example, it does not apply to materials which dissipate energy by friction. For materials obeying Ilyushin's postulate it can be shown that (Hill and Rice, 1973; Havner, 1992)

$$d^p\mathbf{T} : d\mathbf{E} < 0. \quad (9)$$

Since during plastic loading the strain increment $d\mathbf{E}$ is directed outward from the yield surface, and since the same $d^p\mathbf{T}$ is associated with a fan of infinitely many $d\mathbf{E}$ around the normal $\partial g/\partial\mathbf{E}$, all having the same projection on that normal, the inequality (9) requires that $d^p\mathbf{T}$ is codirectional with the inward normal to a locally smooth yield surface in strain space,

$$d^p\mathbf{T} = -d\gamma \frac{\partial g}{\partial\mathbf{E}}. \quad (10)$$

The scalar multiplier $d\gamma > 0$ is called a loading index. At a vertex of the yield surface, $d^p\mathbf{T}$ must lie within the cone of limiting inward normals.

The inequality (9) and the normality rule (10) hold for all pairs of conjugate stress and strain measures, irrespective of the nature of elastic changes caused by plastic deformation, or possible elastic nonlinearities within the yield surface. Also, (10) applies regardless of whether the material is in a hardening or softening range.

If elastic response within the yield surface is nonlinear, Ilyushin's postulate does not imply that the yield surface is necessarily convex. For a linearly elastic response, however, it follows that

$$(\mathbf{E}^0 - \mathbf{E}) : d^p\mathbf{T} > 0, \quad (11)$$

provided that there is no change of elastic stiffness caused by plastic deformation ($d\mathbf{\Lambda} = 0$), or the change is such that $d\mathbf{\Lambda}$ is negative semi-definite. The strain \mathbf{E}^0 is an arbitrary strain state within the yield surface. Since $d^p\mathbf{T}$ is codirectional with the inward normal to a locally smooth yield surface in strain space, (11) implies that the yield surface is convex. The convexity of the yield surface is not an invariant property, because $d\mathbf{\Lambda}$ can be negative definite for some measures (\mathbf{E}, \mathbf{T}) , but not for others.

Plastic stress and strain rates are related by $\dot{\mathbf{T}}^p = -\mathbf{\Lambda} : \dot{\mathbf{E}}^p$, so that, to first order,

$$d^p\mathbf{T} = -\mathbf{\Lambda} : d^p\mathbf{E}. \quad (12)$$

Since for any elastic strain increment $\delta\mathbf{E}$, emanating from a point on the yield surface in strain space and directed inside of it,

$$d^p\mathbf{T} : \delta\mathbf{E} > 0, \quad (13)$$

substitution of (12) into (13) gives

$$d^p\mathbf{E} : \delta\mathbf{T} < 0. \quad (14)$$

Here, $\delta\mathbf{T} = \mathbf{\Lambda} : \delta\mathbf{E}$ is the stress increment from the point on the yield surface in stress space, directed inside of it (elastic unloading increment associated with elastic strain increment $\delta\mathbf{E}$). Inequality (14) holds for any $\delta\mathbf{T}$ directed inside the yield surface. Consequently, $d^p\mathbf{E}$ must be codirectional with the outward normal to a locally smooth yield surface in stress \mathbf{T} space,

$$d^p\mathbf{E} = d\gamma \frac{\partial f}{\partial \mathbf{T}}, \quad d\gamma > 0. \quad (15)$$

At a vertex of the yield surface, $d^p\mathbf{E}$ must lie within the cone of limiting outward normals. Inequality (14) and the normality rule (15) hold for all pairs of conjugate stress and strain measures.

If material is in a hardening range relative to \mathbf{E} and \mathbf{T} , the stress increment $d\mathbf{T}$ producing plastic deformation $d^p\mathbf{E}$ is directed outside the yield surface, satisfying

$$d^p\mathbf{E} : d\mathbf{T} > 0. \quad (16)$$

If material is in the softening range, the stress increment $d\mathbf{T}$ producing plastic deformation $d^p\mathbf{E}$ is directed inside the yield surface, satisfying the reversed

inequality in (16). The normality rule (15) applies to both hardening and softening. Inequality (16) is not measure invariant, since material may be in the hardening range relative to one pair of conjugate stress and strain measures, and in the softening range relative to another pair.

The normals to the yield surfaces in stress and strain space are related by

$$\frac{\partial g}{\partial \mathbf{E}} = \Lambda : \frac{\partial f}{\partial \mathbf{T}}. \quad (17)$$

This follows directly from Eq. (4) by partial differentiation.

2.2 Drucker's Postulate

A non-invariant dual to (8) is

$$\oint_T \mathbf{E} : d\mathbf{T} < 0, \quad (18)$$

requiring that the net complementary work (relative to measures \mathbf{E} and \mathbf{T}) in an isothermal cycle of stress must be negative, if the cycle at some stage involves plastic deformation. Inequality (18) is non-invariant because the value of the integral in (18) depends on the selected measures \mathbf{E} and \mathbf{T} , and the reference state with respect to which they are defined. This is because \mathbf{T} is introduced as a conjugate stress to \mathbf{E} such that, for the same geometry change, $\mathbf{T} : d\mathbf{E}$ (and not $\mathbf{E} : d\mathbf{T}$) is measure invariant. If inequality (18) applies to conjugate pair (\mathbf{E}, \mathbf{T}) , it follows that in the hardening range (16) holds, and $d^p \mathbf{E}$ is codirectional with the outward normal to a locally smooth yield surface

in stress \mathbf{T} space, Eq. (15). At a vertex of the yield surface, $d^p\mathbf{E}$ must lie within the cone of limiting outward normals. In the softening range,

$$d^p\mathbf{E} : d\mathbf{T} < 0. \quad (19)$$

Since $d\mathbf{T}$ is now directed inside the current yield surface, (19) also requires that $d^p\mathbf{E}$ is codirectional with the outward normal to a locally smooth yield surface in stress \mathbf{T} space, with the same generalization at a vertex as in the case of hardening behavior.

If elastic response is nonlinear, the yield surface in stress space is not necessarily convex. A concavity of the yield surface in the presence of nonlinear elasticity for a particular material model has been demonstrated by Palmer, Maier and Drucker (1967). For linear elastic response, however,

$$(\mathbf{T} - \mathbf{T}^0) : d^p\mathbf{E} > 0, \quad (20)$$

provided that there is no change of elastic stiffness caused by plastic deformation ($d\mathbf{M} = 0$), or that the change is such that $d\mathbf{M}$ is positive semi-definite. The stress state \mathbf{T}^0 is an arbitrary stress state within the yield surface. Since $d^p\mathbf{E}$ is codirectional with the outward normal to a locally smooth yield surface in strain \mathbf{T} space, (20) implies that the yield surface in a considered stress space is convex. Inequality (20) is often referred to as the principle of maximum plastic work (Hill, 1950; Johnson and Mellor, 1973; Lubliner, 1990). If inequality is assumed at the outset, it by itself assures both normality and convexity.

3 Constitutive Equations of Elastoplasticity

3.1 Strain Space Formulation

The stress rate is a sum of elastic and plastic parts, such that

$$\dot{\mathbf{T}} = \dot{\mathbf{T}}^e + \dot{\mathbf{T}}^p = \mathbf{\Lambda} : \dot{\mathbf{E}} - \dot{\gamma} \frac{\partial g}{\partial \mathbf{E}}. \quad (21)$$

For incrementally linear and continuous response between loading and unloading, the loading index is

$$\dot{\gamma} = \frac{1}{h} \left(\frac{\partial g}{\partial \mathbf{E}} : \dot{\mathbf{E}} \right), \quad \frac{\partial g}{\partial \mathbf{E}} : \dot{\mathbf{E}} > 0, \quad (22)$$

where $h > 0$ is a scalar function of the plastic state on the yield surface in strain space, determined from the consistency condition $\dot{g} = 0$. Consequently, the constitutive equation for elastoplastic loading is

$$\dot{\mathbf{T}} = \left[\mathbf{\Lambda} - \frac{1}{h} \left(\frac{\partial g}{\partial \mathbf{E}} \otimes \frac{\partial g}{\partial \mathbf{E}} \right) \right] : \dot{\mathbf{E}}. \quad (23)$$

The fourth-order tensor within the square brackets is the elastoplastic stiffness tensor associated with the considered measure and reference state. Within the framework based on Green-elasticity and normality rule, the elastoplastic stiffness tensor possesses reciprocal or self-adjoint symmetry (with respect to first and second pair of indices), in addition to symmetries in the first and last two indices associated with the symmetry of stress and strain tensors.

The inverted form of (23) is

$$\dot{\mathbf{E}} = \left[\mathbf{M} + \frac{1}{H} \left(\mathbf{M} : \frac{\partial g}{\partial \mathbf{E}} \right) \otimes \left(\frac{\partial g}{\partial \mathbf{E}} : \mathbf{M} \right) \right] : \dot{\mathbf{T}}, \quad (24)$$

where

$$H = h - \frac{\partial g}{\partial \mathbf{E}} : \mathbf{M} : \frac{\partial g}{\partial \mathbf{E}}. \quad (25)$$

3.2 Stress Space Formulation

The strain rate is a sum of elastic and plastic parts, such that

$$\dot{\mathbf{E}} = \dot{\mathbf{E}}^e + \dot{\mathbf{E}}^p = \mathbf{M} : \dot{\mathbf{T}} + \dot{\gamma} \frac{\partial f}{\partial \mathbf{T}}. \quad (26)$$

The loading index is obtained from the consistency condition $\dot{f} = 0$,

$$\dot{\gamma} = \frac{1}{H} \left(\frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} \right), \quad (27)$$

where H is a scalar function of the plastic state on the yield surface in stress space. Thus,

$$\dot{\mathbf{E}} = \left[\mathbf{M} + \frac{1}{H} \left(\frac{\partial f}{\partial \mathbf{T}} \otimes \frac{\partial f}{\partial \mathbf{T}} \right) \right] : \dot{\mathbf{T}}. \quad (28)$$

The fourth-order tensor within the square brackets is the elastoplastic compliance tensor associated with the considered measure and reference state.

The scalar parameter H can be positive, negative or equal to zero. Three types of response can be identified within this constitutive framework. These

are (Hill, 1978)

$$\begin{aligned}
H > 0, \quad \frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} > 0 & \text{ hardening,} \\
H < 0, \quad \frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} < 0 & \text{ softening,} \\
H = 0, \quad \frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} = 0 & \text{ ideally plastic.}
\end{aligned} \tag{29}$$

Starting from the current yield surface in stress space, the yield point moves outward in the case of hardening, inward in the case of softening, and tangentially to the yield surface in the case of ideally plastic response. In the case of softening, $\dot{\mathbf{E}}$ is not uniquely determined by prescribed stress rate $\dot{\mathbf{T}}$, since either Eq. (28) applies, or the elastic unloading expression $\dot{\mathbf{E}} = \mathbf{M} : \dot{\mathbf{T}}$. In the case of ideally plastic response, the plastic part of the strain rate is indeterminate to the extent of an arbitrary positive multiple, since $\dot{\gamma}$ in Eq. (27) is indeterminate.

3.3 Yield Surface with a Vertex

Physical theories of plasticity imply the formation of a corner or vertex at the loading point on the yield surface. Suppose that the yield surface in stress space has a pyramidal vertex formed by n intersecting segments $f_{\langle i \rangle} = 0$, then near the vertex

$$\prod_{i=1}^n f_{\langle i \rangle}(\mathbf{T}, \mathcal{H}) = 0, \quad n \geq 2. \tag{30}$$

It follows that

$$\dot{\mathbf{E}} = \left[\mathbf{M} + \sum_{i=1}^n \sum_{j=1}^n H_{\langle ij \rangle}^{-1} \left(\frac{\partial f_{\langle i \rangle}}{\partial \mathbf{T}} \otimes \frac{\partial f_{\langle j \rangle}}{\partial \mathbf{T}} \right) \right] : \dot{\mathbf{T}}. \tag{31}$$

This is an extension of the constitutive structure (28) for the smooth yield surface to the yield surface with a vertex. Elements of the matrix inverse to plastic moduli matrix $H_{\langle ij \rangle}$ are denoted by $H_{\langle ij \rangle}^{-1}$. The papers by Koiter (1953), Hill (1978), and Asaro (1983) can be consulted for further analysis.

4 Constitutive Models of Plastic Deformation

4.1 Isotropic Hardening

Experimental determination of the yield surface shape is commonly done with respect to Cauchy stress $\boldsymbol{\sigma}$. Suppose that this is given by $f(\boldsymbol{\sigma}, k) = 0$, where f is an isotropic function of $\boldsymbol{\sigma}$ and $k = k(\vartheta)$ is a scalar which defines the size of the yield surface. This depends on the history parameter, such as the effective plastic strain

$$\vartheta = \int_0^t (2 \mathbf{D}^p : \mathbf{D}^p)^{1/2} dt. \quad (32)$$

The hardening model in which the yield surface expands during plastic deformation preserving its shape is known as the isotropic hardening model. Since f is an isotropic function of stress, the material is assumed to be isotropic. For non-porous metals the onset of plastic deformation and plastic yielding is unaffected by moderate superimposed pressure. The yield condition can consequently be written as an isotropic function of the deviatoric part of the Cauchy stress, i.e. its second and third invariant, $f(J_2, J_3, k) = 0$. The well-known examples are the Tresca maximum shear stress criterion, or the von

Mises yield criterion. In the latter case,

$$f = J_2 - k^2(\vartheta) = 0, \quad J_2 = \frac{1}{2} \boldsymbol{\sigma}' : \boldsymbol{\sigma}'. \quad (33)$$

The corresponding plasticity theory is referred to as the J_2 flow theory of plasticity. The yield stress in simple shear is k . If Y is the yield stress in uniaxial tension, $k = Y/\sqrt{3}$. The consistency condition gives

$$\dot{\gamma} = \frac{1}{4k^2 h_t^p} (\boldsymbol{\sigma}' : \overset{\circ}{\boldsymbol{\tau}}), \quad H = 4k^2 h_t^p, \quad (34)$$

where the plastic tangent modulus in shear test is $h_t^p = dk/d\vartheta$. The stress rate

$$\overset{\circ}{\boldsymbol{\tau}} = \overset{\circ}{\boldsymbol{\sigma}} + \boldsymbol{\sigma} \operatorname{tr} \mathbf{D}, \quad \overset{\circ}{\boldsymbol{\sigma}} = \dot{\boldsymbol{\sigma}} - \mathbf{W} \cdot \boldsymbol{\sigma} + \boldsymbol{\sigma} \cdot \mathbf{W} \quad (35)$$

represents the Jaumann rate of the Kirchhoff stress $\boldsymbol{\tau} = (\det \mathbf{F})\boldsymbol{\sigma}$, when the current state is taken as the reference ($\det \mathbf{F} = 0$). The deformation gradient is \mathbf{F} , and the material spin is \mathbf{W} . The total rate of deformation is therefore

$$\mathbf{D} = \left(\mathbf{M} + \frac{1}{2h_t^p} \frac{\boldsymbol{\sigma}' \otimes \boldsymbol{\sigma}'}{\boldsymbol{\sigma}' : \boldsymbol{\sigma}'} \right) : \overset{\circ}{\boldsymbol{\tau}}. \quad (36)$$

The elastic compliance tensor for infinitesimal elasticity is

$$\mathbf{M} = \frac{1}{2\mu} \left(\mathbf{I} - \frac{\lambda}{2\mu + 3\lambda} \boldsymbol{\delta} \otimes \boldsymbol{\delta} \right). \quad (37)$$

The Lamé elastic constants are λ and μ . The second- and fourth-order unit tensors are designated by $\boldsymbol{\delta}$ and \mathbf{I} . The plastic deformation is in this case isochoric ($\operatorname{tr} \mathbf{D}^p = 0$), and principal directions of \mathbf{D}^p are parallel to those of $\boldsymbol{\sigma}$

($\mathbf{D}^p \sim \boldsymbol{\sigma}'$). The inverted form of (36) is

$$\overset{\circ}{\boldsymbol{\tau}} = \left(\boldsymbol{\Lambda} - \frac{2\mu}{1 + h_t^p/\mu} \frac{\boldsymbol{\sigma}' \otimes \boldsymbol{\sigma}'}{\boldsymbol{\sigma}' : \boldsymbol{\sigma}'} \right) : \mathbf{D}, \quad (38)$$

where

$$\boldsymbol{\Lambda} = \lambda \boldsymbol{\delta} \otimes \boldsymbol{\delta} + 2\mu \mathbf{I} \quad (39)$$

is the elastic stiffness tensor. Constitutive structures (36) and (38) have been extensively used in analytical and numerical studies of large plastic deformation problems (Neale, 1981; Needleman, 1982). Infinitesimal strain formulation, derivation of classical Prandtl-Reuss equations for elastic-ideally plastic, and Levy-Mises equations for rigid-ideally plastic material models can be found in standard texts or review papers (Hill, 1950; Naghdi, 1960).

4.2 Kinematic Hardening

To account for the Bauschinger effect and anisotropy of hardening, a simple model of kinematic hardening was introduced by Prager (1956). According to this model, the initial yield surface does not change its size and shape during plastic deformation, but translates in the stress space according to some prescribed rule. Thus, $f(\boldsymbol{\sigma} - \boldsymbol{\alpha}, k) = 0$, where $\boldsymbol{\alpha}$ represents the current center of the yield surface (back stress), and f is an isotropic function of the stress difference $\boldsymbol{\sigma} - \boldsymbol{\alpha}$. The size of the yield surface is specified by the constant k . The evolution of the back stress is governed by

$$\overset{\circ}{\boldsymbol{\alpha}} = c(\boldsymbol{\alpha}) \mathbf{D}^p + \mathbf{C}(\boldsymbol{\alpha}) (2\mathbf{D}^p : \mathbf{D}^p)^{1/2}, \quad (40)$$

where c and \mathbf{C} are appropriate scalar and tensor functions of $\boldsymbol{\alpha}$. This representation is in accord with assumed time independence of plastic deformation, which requires Eq. (40) to be homogeneous relation of degree one.

If $\mathbf{C} = 0$ and c is taken to be constant, the model corresponds to Prager's linear kinematic hardening. The plastic tangent modulus h_t^p in shear test is in this case constant and related to c by $c = 2h_t^p$. The resulting constitutive structure is

$$\mathbf{D} = \left[\mathbf{M} + \frac{1}{2h_t^p} \frac{(\boldsymbol{\sigma}' - \boldsymbol{\alpha}) \otimes (\boldsymbol{\sigma}' - \boldsymbol{\alpha})}{(\boldsymbol{\sigma}' - \boldsymbol{\alpha}) : (\boldsymbol{\sigma}' - \boldsymbol{\alpha})} \right] : \overset{\circ}{\boldsymbol{\varepsilon}}, \quad (41)$$

with the inverse

$$\overset{\circ}{\boldsymbol{\varepsilon}} = \left[\boldsymbol{\Lambda} - \frac{2\mu}{1 + h_t^p/\mu} \frac{(\boldsymbol{\sigma}' - \boldsymbol{\alpha}) \otimes (\boldsymbol{\sigma}' - \boldsymbol{\alpha})}{(\boldsymbol{\sigma}' - \boldsymbol{\alpha}) : (\boldsymbol{\sigma}' - \boldsymbol{\alpha})} \right] : \mathbf{D}. \quad (42)$$

If \mathbf{C} in Eq. (40) is taken to be proportional to $\boldsymbol{\alpha}$ (i.e., $\mathbf{C} = -c_0 \boldsymbol{\alpha}$, $c_0 = \text{const.}$), a nonlinear kinematic hardening model of Armstrong and Frederick (1966) is obtained. Details can be found in Khan and Huang (1995). Ziegler (1959) used as an evolution equation for the back stress

$$\overset{\circ}{\boldsymbol{\alpha}} = \dot{\beta} (\boldsymbol{\sigma}' - \boldsymbol{\alpha}). \quad (43)$$

The proportionality factor $\dot{\beta}$ is determined from the consistency condition in terms of $\boldsymbol{\sigma}$ and $\boldsymbol{\alpha}$.

4.3 Combined Isotropic-Kinematic Hardening

In this hardening model the yield surface expands and translates during plastic deformation, so that

$$f(\boldsymbol{\sigma} - \boldsymbol{\alpha}, k) = 0, \quad k = k(\vartheta). \quad (44)$$

The function $k(\vartheta)$, with ϑ defined by Eq. (32), specifies expansion of the yield surface, while evolution equation (40) specifies its translation.

4.4 Multisurface Models

Motivated by the need to better model nonlinearities in stress-strain loops, cyclic hardening or softening, cyclic creep and stress relaxation, more involved hardening models were suggested. Mróz (1967) introduced a multi-yield surface model in which there is a field of hardening moduli, one for each yield surface. Initially the yield surfaces are assumed to be concentric. When the stress point reaches the inner-most yield surface, the plastic deformation develops according to linear hardening model with a prescribed plastic tangent modulus, until the active yield surface reaches the adjacent yield surface. Subsequent plastic deformation develops according to linear hardening model with another specified value of the plastic tangent modulus, until the next yield surface is reached, etc.. Dafalias and Popov (1975) and Krieg (1975) suggested a hardening model which uses the yield (loading) surface and the limit (bounding) surface. A smooth transition from elastic to plastic regions on loading is

assured by introducing a continuous variation of the plastic tangent modulus between the two surfaces.

5 Pressure-Dependent Plasticity

For porous metals, concrete and geomaterials like soils and rocks, plastic deformation has its origin in pressure dependent microscopic processes and the yield condition for these materials, in addition to deviatoric components, depends on hydrostatic component of stress, i.e. its first invariant $I_1 = \text{tr } \boldsymbol{\sigma}$.

5.1 Drucker-Prager Yield Condition for Geomaterials

Drucker and Prager (1952) suggested that yielding of soil occurs when the shear stress on octahedral planes overcomes cohesive and frictional resistance to sliding on those planes. The yield condition is consequently

$$f = J_2^{1/2} + \frac{1}{3} \alpha I_1 - k = 0, \quad (45)$$

where α is a frictional parameter. This geometrically represents a cone in the principal stress space with its axis parallel to hydrostatic axis. The radius of the circle in the deviatoric plane is $\sqrt{2} k$, where k is the yield stress in simple shear. The angle of the cone is $\tan^{-1}(\sqrt{2} \alpha / 3)$. The yield stresses in uniaxial tension and compression are according to Eq. (45),

$$Y^+ = \frac{\sqrt{3} k}{1 + \alpha/\sqrt{3}}, \quad Y^- = \frac{\sqrt{3} k}{1 - \alpha/\sqrt{3}}. \quad (46)$$

For the yield condition to be physically meaningful, the restriction holds $\alpha < \sqrt{3}$. If the compressive states of stress are considered positive (as commonly done in geomechanics), the minus sign appears in front of the second term in Eq. (45).

When Drucker-Prager cone is applied to porous rocks, it overestimates the yield stress at higher pressures and inadequately predicts inelastic volume changes. To circumvent this, DiMaggio and Sandler (1971) introduced an ellipsoidal cap to close the cone at certain level of pressure. Other shapes of the cap were also used. Details can be found in Chen and Han (1988).

5.2 Gurson Yield Condition for Porous Metals

Based on a rigid-perfectly plastic analysis of spherically symmetric deformation around a spherical cavity, Gurson (1977) suggested a yield condition for porous metals in the form

$$f = J_2 + \frac{2}{3} v Y_0^2 \cosh\left(\frac{I_1}{2Y_0}\right) - (1 + v^2) \frac{Y_0^2}{3} = 0, \quad (47)$$

where v is the porosity (void/volume fraction), and $Y_0 = \text{const.}$ is the tensile yield stress of the matrix material. Generalizations to include hardening matrix material were also made. The change in porosity during plastic deformation is given by the evolution equation

$$\dot{v} = (1 - v) \text{tr } \mathbf{D}^P. \quad (48)$$

Other evolution equations, which take into account nucleation and growth of voids, have been considered. To improve its predictions and agreement with experimental data, Tvergaard (1982) introduced two additional material parameters in the structure of the Gurson yield criterion. Mear and Hutchinson (1985) incorporated the effects of anisotropic (kinematic) hardening by replacing J_2 of $\boldsymbol{\sigma}'$ in Eq. (47) with J_2 of $\boldsymbol{\sigma}' - \boldsymbol{\alpha}$, where $\boldsymbol{\alpha}$ is the back stress.

5.3 Constitutive Equations of Pressure-Dependent Plasticity

The two considered pressure-dependent yield conditions are of the type

$$f(J_2, I_1, \mathcal{H}) = 0. \quad (49)$$

For materials obeying Ilyushin's postulate, the plastic part of the rate of deformation tensor is normal to the yield surface, so that

$$\mathbf{D}^p = \dot{\gamma} \frac{\partial f}{\partial \boldsymbol{\sigma}}, \quad \frac{\partial f}{\partial \boldsymbol{\sigma}} = \frac{\partial f}{\partial J_2} \boldsymbol{\sigma}' + \frac{\partial f}{\partial I_1} \boldsymbol{\delta}. \quad (50)$$

The loading index is

$$\dot{\gamma} = \frac{1}{H} \left(\frac{\partial f}{\partial J_2} \boldsymbol{\sigma}' + \frac{\partial f}{\partial I_1} \boldsymbol{\delta} \right) : \overset{\circ}{\boldsymbol{\varepsilon}}, \quad (51)$$

where H is an appropriate hardening modulus. Therefore,

$$\mathbf{D}^p = \frac{1}{H} \left[\left(\frac{\partial f}{\partial J_2} \boldsymbol{\sigma}' + \frac{\partial f}{\partial I_1} \boldsymbol{\delta} \right) \otimes \left(\frac{\partial f}{\partial J_2} \boldsymbol{\sigma}' + \frac{\partial f}{\partial I_1} \boldsymbol{\delta} \right) \right] : \overset{\circ}{\boldsymbol{\varepsilon}}. \quad (52)$$

The volumetric part of the plastic rate of deformation is

$$\text{tr} \mathbf{D}^p = \frac{3}{H} \frac{\partial f}{\partial I_1} \left(\frac{\partial f}{\partial J_2} \boldsymbol{\sigma}' + \frac{\partial f}{\partial I_1} \boldsymbol{\delta} \right) : \overset{\circ}{\boldsymbol{\varepsilon}}. \quad (53)$$

For the Drucker-Prager yield condition,

$$\frac{\partial f}{\partial J_2} = \frac{1}{2} J_2^{-1/2}, \quad \frac{\partial f}{\partial I_1} = \frac{1}{3} \alpha, \quad (54)$$

and

$$H = \frac{dk}{d\vartheta}, \quad \vartheta = \int_0^t (2 \mathbf{D}^{p'} : \mathbf{D}^{p'})^{1/2} dt. \quad (55)$$

For the Gurson yield condition,

$$\frac{\partial f}{\partial J_2} = 1, \quad \frac{\partial f}{\partial I_1} = \frac{1}{3} v Y_0 \sinh \left(\frac{I_1}{2Y_0} \right), \quad (56)$$

and

$$H = \frac{2}{3} v(1-v) Y_0^3 \sinh \left(\frac{I_1}{2Y_0} \right) \left[v - \cosh \left(\frac{I_1}{2Y_0} \right) \right]. \quad (57)$$

6 Non-Associative Plasticity

Constitutive equations in which plastic part of the rate of strain is normal to locally smooth yield surface $f = 0$ in stress space,

$$\dot{\mathbf{E}}^p = \dot{\gamma} \frac{\partial f}{\partial \mathbf{T}}, \quad (58)$$

are often referred to as associative flow rules. A sufficient condition for this constitutive structure to hold is that material obeys the Ilyushin's postulate. However, many pressure-dependent dilatant materials with internal frictional effects are not well described by associative flow rules. For example, associative flow rules largely overestimate inelastic volume changes in geomaterials like rocks and soils (Rudnicki and Rice, 1975), and in certain high-strength steels exhibiting the strength-differential effect by which the yield strength is higher

in compression than in tension (Spitzig, Sober and Richmond, 1975). For such materials, plastic part of the rate of strain is taken to be normal to plastic potential surface $\pi = 0$, which is distinct from the yield surface. The resulting constitutive structure,

$$\dot{\mathbf{E}}^p = \dot{\gamma} \frac{\partial \pi}{\partial \mathbf{T}}, \quad (59)$$

is known as non-associative flow rule (Nemat-Nasser, 1983). The consistency condition $\dot{f} = 0$ gives

$$\dot{\gamma} = \frac{1}{H} \frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}}, \quad (60)$$

so that

$$\dot{\mathbf{E}}^p = \frac{1}{H} \left(\frac{\partial \pi}{\partial \mathbf{T}} \otimes \frac{\partial f}{\partial \mathbf{T}} \right) : \dot{\mathbf{T}}. \quad (61)$$

Since $\pi \neq f$, the plastic compliance tensor in Eq. (61) does not possess a reciprocal symmetry.

Consider inelastic behavior of geomaterials whose yield is governed by the Drucker-Prager yield condition of Eq. (45). A non-associative flow rule can be used with the plastic potential

$$\pi = J_2^{1/2} + \frac{1}{3} \beta I_1 - k = 0. \quad (62)$$

The material parameter β is in general different from the frictional parameter α of Eq. (45). The rate of plastic deformation is

$$\mathbf{D}^p = \dot{\gamma} \frac{\partial \pi}{\partial \boldsymbol{\sigma}} = \dot{\gamma} \left(\frac{1}{2} J_2^{-1/2} \boldsymbol{\sigma}' + \frac{1}{3} \beta \boldsymbol{\delta} \right). \quad (63)$$

The consistency condition $\dot{f} = 0$ gives the loading index

$$\dot{\gamma} = \frac{1}{H} \left(\frac{1}{2} J_2^{-1/2} \boldsymbol{\sigma}' + \frac{1}{3} \alpha \boldsymbol{\delta} \right) : \overset{\circ}{\boldsymbol{\varepsilon}}, \quad H = \frac{dk}{d\vartheta}. \quad (64)$$

Consequently,

$$\mathbf{D}^p = \frac{1}{H} \left[\left(\frac{1}{2} J_2^{-1/2} \boldsymbol{\sigma}' + \frac{1}{3} \beta \boldsymbol{\delta} \right) \otimes \left(\frac{1}{2} J_2^{-1/2} \boldsymbol{\sigma}' + \frac{1}{3} \alpha \boldsymbol{\delta} \right) \right] : \overset{\circ}{\boldsymbol{\varepsilon}}. \quad (65)$$

The deviatoric and spherical parts are

$$\mathbf{D}^{p'} = \frac{1}{2H} \frac{\boldsymbol{\sigma}'}{J_2^{1/2}} \left(\frac{\boldsymbol{\sigma}' : \overset{\circ}{\boldsymbol{\varepsilon}}}{2 J_2^{1/2}} + \frac{1}{3} \alpha \operatorname{tr} \overset{\circ}{\boldsymbol{\varepsilon}} \right), \quad (66)$$

$$\operatorname{tr} \mathbf{D}^p = \frac{\beta}{H} \left(\frac{\boldsymbol{\sigma}' : \overset{\circ}{\boldsymbol{\varepsilon}}}{2 J_2^{1/2}} + \frac{1}{3} \alpha \operatorname{tr} \overset{\circ}{\boldsymbol{\varepsilon}} \right). \quad (67)$$

The parameter β can be expressed as

$$\beta = \frac{\operatorname{tr} \mathbf{D}^p}{(2 \mathbf{D}^{p'} : \mathbf{D}^{p'})^{1/2}}, \quad (68)$$

which shows that β is the ratio of the volumetric and shear part of the plastic strain rate, often called the dilatancy factor (Rudnicki and Rice, 1975). Frictional parameter and inelastic dilatancy of material actually change with progression of inelastic deformation. An analysis which accounts for their variation is presented by Nemat-Nasser and Shokooh (1980). Constitutive formulation of elastoplastic theory with evolving elastic properties is considered by Lubarda and Krajcinovic (1995).

6.1 *Yield Vertex Model for Fissured Rocks*

In a brittle rock, modeled to contain a collection of randomly oriented fissures, inelastic deformation results from frictional sliding on the fissure surfaces. Inelastic dilatancy under overall compressive loads is a consequence of opening the fissures at asperities and local tensile fractures at some angle at the edges of fissures. Individual yield surface may be associated with each fissure. The macroscopic yield surface is the envelope of individual yield surfaces for fissures of all orientations, similarly to slip models of metal plasticity (Rudnicki and Rice, 1975; Rice, 1976). Continued stressing in the same direction will cause continuing sliding on (already activated) favorably oriented fissures, and will initiate sliding for a progressively greater number of orientations. After certain amount of inelastic deformation, the macroscopic yield envelope develops a vertex at the loading point. The stress increment normal to the original stress direction will initiate or continue sliding of fissure surfaces for some fissure orientations. In isotropic hardening idealization with smooth yield surface, however, a stress increment tangential to the yield surface will cause only elastic deformation, overestimating the stiffness of response. In order to take into account the effect of the yield vertex in an approximate way, a second plastic modulus H_1 is introduced, which governs the response to part of the stress increment directed tangentially to what is taken to be the smooth yield surface through the same stress point. Since no vertex formation is associated with hydrostatic stress increments, tangential stress increments are taken to

be deviatoric, and Eq. (66) is replaced with

$$\mathbf{D}^{p'} = \frac{1}{2H} \frac{\boldsymbol{\sigma}'}{J_2^{1/2}} \left(\frac{\boldsymbol{\sigma}' : \overset{\circ}{\boldsymbol{\varepsilon}}}{2J_2^{1/2}} + \frac{1}{3} \alpha \operatorname{tr} \overset{\circ}{\boldsymbol{\varepsilon}} \right) + \frac{1}{2H_1} \left(\overset{\circ}{\boldsymbol{\varepsilon}}' - \frac{\boldsymbol{\sigma}' : \overset{\circ}{\boldsymbol{\varepsilon}}}{2J_2} \boldsymbol{\sigma}' \right). \quad (69)$$

The dilation induced by the small tangential stress increment is assumed to be negligible, so that Eq. (67) applies for $\operatorname{tr} \mathbf{D}^p$. The constitutive structure of Eq. (69) is intended to model the response at a yield surface vertex for small deviations from proportional (straight ahead) loading $\overset{\circ}{\boldsymbol{\varepsilon}} \sim \boldsymbol{\sigma}'$. For the full range of directions of stress increment, the relationship between the rates of stress and plastic deformation is not expected to be necessarily linear, although it is homogeneous in these rates in the absence of time-dependent creep effects.

7 Deformation Theory of Plasticity

Simple plasticity theory has been suggested for proportional loading and small deformation by Hencky (1924) and Ilyushin (1963). A large deformation version of the theory can be formulated by using the logarithmic strain and its conjugate stress. Since stress proportionally increase, elastoplastic response is described macroscopically by constitutive structure of nonlinear elasticity, where strain is a function of stress. The strain tensor is decomposed into elastic and plastic part, $\mathbf{E} = \mathbf{E}^e + \mathbf{E}^p$, elastic part is expressed in terms of stress by generalized Hooke's law, and plastic part is assumed to be

$$\mathbf{E}^p = \varphi \mathbf{T}', \quad (70)$$

where φ is an appropriate scalar function. Suppose that a nonlinear relationship $\bar{\tau} = \bar{\tau}(\bar{\gamma}^p)$ is available from the elastoplastic shear test. Define the plastic secant and tangent moduli by $h_s^p = \bar{\tau}/\bar{\gamma}^p$, $h_t^p = d\bar{\tau}/d\bar{\gamma}^p$, and let

$$\bar{\tau} = \left(\frac{1}{2} \mathbf{T}' : \mathbf{T}' \right)^{1/2}, \quad \bar{\gamma}^p = (2 \mathbf{E}^p : \mathbf{E}^p)^{1/2}. \quad (71)$$

The scalar function φ is then $\varphi = 1/2h_s^p$. Although deformation theory of plasticity is total strain theory, it is useful to cast it in the rate-type form, particularly when the considered boundary value problem needs to be solved in an incremental manner. The resulting expression for the plastic part of the total rate of deformation is

$$\mathbf{D}^p = \frac{1}{2h_s^p} \overset{\circ}{\boldsymbol{\tau}}' + \left(\frac{1}{2h_t^p} - \frac{1}{2h_s^p} \right) \frac{(\boldsymbol{\tau}' \otimes \boldsymbol{\tau}') : \overset{\circ}{\boldsymbol{\tau}}}{\boldsymbol{\tau}' : \boldsymbol{\tau}'}, \quad (72)$$

where $\overset{\circ}{\boldsymbol{\tau}}$ is the Jaumann derivative of the Kirchhoff stress.

7.1 Application of Deformation Theory Beyond Proportional Loading

Deformation theory agrees with flow theory of plasticity only under proportional loading, since then specification of the final state of stress also specifies the stress history. For general (non-proportional) loading, more accurate and physically appropriate is the flow theory of plasticity, particularly with an accurate modelling of the yield surface and hardening behavior. Budiansky (1959), however, indicated that deformation theory can be successfully used for certain nearly proportional loading paths, as well. The stress rate $\overset{\circ}{\boldsymbol{\tau}}'$ in Eq. (72) does not then have to be codirectional with $\boldsymbol{\tau}'$, and the plastic part of the

rate of deformation depends on both components of the stress rate $\overset{\circ}{\boldsymbol{\tau}}'$, one in the direction of $\boldsymbol{\tau}'$ and the other normal to it. In contrast, according to flow theory with the von Mises smooth yield surface, the component of the stress rate $\overset{\circ}{\boldsymbol{\tau}}'$ normal to $\boldsymbol{\tau}'$ (thus tangential to the yield surface) does not affect the plastic part of the rate of deformation. Since the structure of the deformation theory of plasticity under proportional loading does not use any notion of the yield surface, Eq. (72) can be used to approximately describe the response when the yield surface develops a vertex. Rewriting Eq. (72) in the form

$$\mathbf{D}^p = \frac{1}{2h_s^p} \left[\overset{\circ}{\boldsymbol{\tau}}' - \frac{(\boldsymbol{\tau}' \otimes \boldsymbol{\tau}') : \overset{\circ}{\boldsymbol{\tau}}'}{\boldsymbol{\tau}' : \boldsymbol{\tau}'} \right] + \frac{1}{2h_t^p} \frac{(\boldsymbol{\tau}' \otimes \boldsymbol{\tau}') : \overset{\circ}{\boldsymbol{\tau}}'}{\boldsymbol{\tau}' : \boldsymbol{\tau}'}, \quad (73)$$

the first term on the right-hand side gives the response to component of the stress increment normal to $\boldsymbol{\tau}'$. The associated plastic modulus is h_s^p . The plastic modulus associated with the component of the stress increment in the direction of $\boldsymbol{\tau}'$ is h_t^p . A corner theory that predicts continuous variation of the stiffness and allows increasingly non-proportional increments of stress was formulated by Christoffersen and Hutchinson (1979). When applied to the analysis of necking in thin sheets under biaxial stretching, the results were in better agreement with experiments than those obtained from the theory with smooth yield characterization. Similar observations were long known in the field of elastoplastic buckling. Deformation theory predicts buckling loads better than flow theory with a smooth yield surface (Hutchinson, 1974).

8 Thermoplasticity

Non-isothermal plasticity is here considered assuming that temperature is not too high, so that creep deformation can be neglected. The analysis may also be adequate for certain applications under high stresses of short duration, where temperature increase is more pronounced but viscous (creep) strains have no time to develop (Prager, 1958; Kachanov, 1971). Thus, infinitesimal changes of stress and temperature applied to the material at a given state produce a unique infinitesimal change of strain that is independent of the speed with which these changes are made. Rate-dependent plasticity models will be presented in Section 9.

The formulation of thermoplastic analysis under described conditions can proceed by introducing a non-isothermal yield condition in either stress or strain space. For example, the yield condition in stress space is $f(\mathbf{T}, \theta, \mathcal{H}) = 0$. The response within the yield surface is thermoelastic. If the Gibbs energy relative to selected stress and strain measures is $\phi = \phi(\mathbf{T}, \theta, \mathcal{H})$ per unit reference volume, the strain is $\mathbf{E} = \partial\phi/\partial\mathbf{T}$.

Let the stress state \mathbf{T} be on the current yield surface. The rates of stress and temperature associated with thermoplastic loading satisfy the consistency condition $\dot{f} = 0$, which gives

$$\frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} + \frac{\partial f}{\partial \theta} : \dot{\theta} - \dot{\gamma}H = 0. \quad (74)$$

The hardening parameter is $H = H(\mathbf{T}, \theta, \mathcal{H})$, and the loading index is $\dot{\gamma} > 0$.

Three types of response are possible,

$$\begin{aligned} H > 0, \quad \frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} + \frac{\partial f}{\partial \theta} : \dot{\theta} > 0 & \text{ thermoplastic hardening,} \\ H < 0, \quad \frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} + \frac{\partial f}{\partial \theta} : \dot{\theta} < 0 & \text{ thermoplastic softening,} \\ H = 0, \quad \frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} + \frac{\partial f}{\partial \theta} : \dot{\theta} = 0 & \text{ ideally thermoplastic.} \end{aligned} \quad (75)$$

This parallels the isothermal classification of Eq. (29).

Since rate-independence is assumed, the constitutive relationship has to be homogeneous of degree one in rates of stress, strain and temperature. For thermoplastic part of the rate of strain this is satisfied by the normality structure

$$\dot{\mathbf{E}}^p = \dot{\gamma} \frac{\partial f}{\partial \mathbf{T}}, \quad (76)$$

which, in view of Eq. (74), becomes

$$\dot{\mathbf{E}}^p = \frac{1}{H} \left(\frac{\partial f}{\partial \mathbf{T}} : \dot{\mathbf{T}} + \frac{\partial f}{\partial \theta} : \dot{\theta} \right) \frac{\partial f}{\partial \mathbf{T}}. \quad (77)$$

The strain rate is a sum of thermoelastic and thermoplastic parts. The thermoelastic part is

$$\dot{\mathbf{E}}^e = \frac{\partial^2 \phi}{\partial \mathbf{T} \otimes \partial \mathbf{T}} : \dot{\mathbf{T}} + \frac{\partial^2 \phi}{\partial \mathbf{T} \partial \theta} \dot{\theta}. \quad (78)$$

For example, if

$$\phi = \frac{1}{4\mu} \left(\text{tr} \mathbf{T}^2 - \frac{\lambda}{3\lambda + 2\mu} \text{tr}^2 \mathbf{T} \right) + \alpha(\theta) \text{tr} \mathbf{T} + \beta(\theta, \mathcal{H}), \quad (79)$$

there follows

$$\dot{\mathbf{E}}^e = \frac{1}{2\mu} \left(\mathbf{I} - \frac{\lambda}{2\mu + 3\lambda} \boldsymbol{\delta} \otimes \boldsymbol{\delta} \right) : \dot{\mathbf{T}} + \alpha'(\theta) \dot{\theta} \boldsymbol{\delta}, \quad (80)$$

where λ and β are the Lamé type elastic constants corresponding to selected measures, α and β are appropriate functions of indicated arguments, and $\alpha' = d\alpha/d\theta$.

Suppose that non-isothermal yield condition in the Cauchy stress space is temperature dependent von Mises condition

$$f = \frac{1}{2} \boldsymbol{\sigma}' : \boldsymbol{\sigma}' - [\varphi(\theta) k(\vartheta)]^2 = 0. \quad (81)$$

The thermoplastic part of the deformation rate is then

$$\mathbf{D}^p = \frac{1}{2\varphi h_t^p} \left(\frac{\boldsymbol{\sigma}' \otimes \boldsymbol{\sigma}'}{\boldsymbol{\sigma}' : \boldsymbol{\sigma}'} : \overset{\circ}{\boldsymbol{\tau}} - \boldsymbol{\sigma}' \frac{\varphi'}{\varphi} \dot{\theta} \right), \quad (82)$$

where $h_t^p = dk/d\vartheta$, and $\varphi' = d\varphi/d\theta$. Combining with Eq. (80), the total rate of deformation is

$$\begin{aligned} \mathbf{D} &= \left[\frac{1}{2\mu} \left(\mathbf{I} - \frac{\lambda}{2\mu + 3\lambda} \boldsymbol{\delta} \otimes \boldsymbol{\delta} \right) + \frac{1}{2\varphi h_t^p} \frac{\boldsymbol{\sigma}' \otimes \boldsymbol{\sigma}'}{\boldsymbol{\sigma}' : \boldsymbol{\sigma}'} \right] : \overset{\circ}{\boldsymbol{\tau}} \\ &+ \left[\alpha'(\theta) \boldsymbol{\delta} - \frac{\varphi'}{2\varphi^2 h_t^p} \boldsymbol{\sigma}' \right] \dot{\theta}. \end{aligned} \quad (83)$$

The inverse equation is

$$\begin{aligned} \overset{\circ}{\boldsymbol{\tau}} &= \left(\lambda \boldsymbol{\delta} \otimes \boldsymbol{\delta} + 2\mu \mathbf{I} - \frac{2\mu}{1 + \varphi h_t^p / \mu} \frac{\boldsymbol{\sigma}' \otimes \boldsymbol{\sigma}'}{\boldsymbol{\sigma}' : \boldsymbol{\sigma}'} \right) : \mathbf{D} \\ &- \left[(3\lambda + 2\mu) \alpha' \boldsymbol{\delta} - \frac{1}{1 + \varphi h_t^p / \mu} \frac{\varphi'}{\varphi} \boldsymbol{\sigma}' \right] \dot{\theta}. \end{aligned} \quad (84)$$

Infinitesimal strain formulation for rigid-thermoplastic material was given by Prager (1958). See also Lee (1969), and Naghdi (1990). Experimental investigation of non-isothermal yield surfaces was reported by Phillips (1982).

In the case of thermoplasticity with linear kinematic hardening ($c = 2h_t^p$), and the temperature-dependent yield surface

$$f = \frac{1}{2} (\boldsymbol{\sigma}' - \boldsymbol{\alpha}) : (\boldsymbol{\sigma}' - \boldsymbol{\alpha}) - [\varphi(\theta)k]^2 = 0, \quad k = \text{const.}, \quad (85)$$

there follows

$$\mathbf{D}^p = \frac{1}{2h_t^p} \left[\frac{(\boldsymbol{\sigma}' - \boldsymbol{\alpha}) \otimes (\boldsymbol{\sigma}' - \boldsymbol{\alpha})}{(\boldsymbol{\sigma}' - \boldsymbol{\alpha}) : (\boldsymbol{\sigma}' - \boldsymbol{\alpha})} : \dot{\boldsymbol{\epsilon}} - \frac{\varphi'}{\varphi} (\boldsymbol{\sigma}' - \boldsymbol{\alpha}) \dot{\theta} \right]. \quad (86)$$

9 Rate-Dependent Plasticity

This section is devoted to inelastic constitutive equations for metals in the strain rate sensitive range of material response, where time effects play an important role. There is an indication from the dislocation dynamics point of view (Johnston and Gilman, 1959) that plasticity caused by crystallographic slip in metals is inherently time-dependent. Once it is assumed that the rate of shearing on a given slip system depends on local stresses only through the resolved shear stress in slip direction, the plastic part of the rate of strain is derivable from a scalar flow potential (Rice, 1971) as

$$\dot{\mathbf{E}}^p = \frac{\partial \Omega(\mathbf{T}, \theta, \mathcal{H})}{\partial \mathbf{T}}. \quad (87)$$

The history of deformation is represented by the pattern of internal rearrangements \mathcal{H} , and the absolute temperature is θ . Geometrically, the plastic part of the strain rate is normal to surfaces of constant flow potential in stress space. There is no yield surface in the model and plastic deformation commences from the onset of loading. Time-independent behavior can be recovered, under certain idealizations – neglecting creep and rate effects, as an appropriate limit (Rice, 1970).

9.1 Power-Law and Johnson-Cook Models

The power-law representation of the flow potential in the Cauchy stress space is

$$\Omega = \frac{2\dot{\gamma}^0}{m+1} \left(\frac{J_2^{1/2}}{k} \right)^m J_2^{1/2}, \quad J_2 = \frac{1}{2} \boldsymbol{\sigma}' : \boldsymbol{\sigma}', \quad (88)$$

where $k = k(\theta, \mathcal{H})$ is the reference shear stress, $\dot{\gamma}^0$ is the reference shear strain rate to be selected for each material, and m is the material parameter (of the order of 100 for metals at room temperature and strain rates below 10^4 s^{-1} ; Nemat-Nasser (1992)). The corresponding plastic part of the rate of deformation is

$$\mathbf{D}^p = \dot{\gamma}^0 \left(\frac{J_2^{1/2}}{k} \right)^m \frac{\boldsymbol{\sigma}'}{J_2^{1/2}}. \quad (89)$$

The equivalent plastic strain is usually used as the only history parameter \mathcal{H} , and the reference shear stress depends on ϑ and θ according to

$$k = k^0 \left(1 + \frac{\vartheta}{\vartheta^0} \right)^\alpha \exp \left(-\beta \frac{\theta - \theta_0}{\theta_m - \theta_0} \right). \quad (90)$$

Here, k^0 and ϑ^0 are the normalizing stress and strain, θ_0 and θ_m are the room and melting temperatures, and α and β are the material parameters. From the onset of loading the deformation rate consists of elastic and plastic constituents, although for large m the plastic contribution may be small if J_2 is less than k .

Another representation of the flow potential, constructed according to Johnson and Cook (1983) model, is

$$\Omega = \frac{2\dot{\gamma}^0}{a} k \exp \left[a \left(\frac{J_2^{1/2}}{k} - 1 \right) \right]. \quad (91)$$

The reference shear stress is

$$k = k^0 \left[1 + b \left(\frac{\vartheta}{\vartheta^0} \right)^c \right] \left[1 - \left(\frac{\theta - \theta_0}{\theta_m - \theta_0} \right)^d \right], \quad (92)$$

where a, b, c, d are the material parameters. The corresponding plastic part of the rate of deformation is in this case

$$\mathbf{D}^p = \dot{\gamma}^0 \exp \left[a \left(\frac{J_2^{1/2}}{k} - 1 \right) \right] \frac{\boldsymbol{\sigma}'}{J_2^{1/2}}. \quad (93)$$

9.2 Viscoplasticity Models

For high strain rate applications in dynamic plasticity (Cristescu, 1967; Clifton, 1983), the flow potential can be taken as

$$\Omega = \frac{1}{\zeta} \left[J_2^{1/2} - k_s(\vartheta) \right]^2, \quad (94)$$

where ζ is the viscosity coefficient, and $k_s(\vartheta)$ represents the shear stress – plastic strain relationship from the (quasi) static shear test. The positive difference $J_2^{1/2} - k_s(\vartheta)$ between the measure of the current dynamic stress state and corresponding static stress state (at the given level of equivalent plastic strain ϑ) is known as the overstress measure (Malvern, 1951). The plastic part of the rate of deformation is

$$\mathbf{D}^p = \frac{1}{\zeta} [J_2^{1/2} - k_s(\vartheta)] \frac{\boldsymbol{\sigma}'}{J_2^{1/2}}. \quad (95)$$

The inverted form of Eq. (95) is

$$\boldsymbol{\sigma}' = \zeta \mathbf{D}^p + 2k_s(\vartheta) \frac{\mathbf{D}^p}{(2\mathbf{D}^p : \mathbf{D}^p)^{1/2}}, \quad (96)$$

which shows that the rate-dependence in the model comes from the first term on the right-hand side. In quasi-static tests, viscosity ζ is taken to be equal to zero, and Eq. (96) reduces to time-independent von-Mises isotropic hardening plasticity. In this case, flow potential Ω is constant within the elastic range bounded by the yield surface $J_2^{1/2} = k_s(\vartheta)$.

More general representation for Ω is possible by using the Perzyna (1966) viscoplastic model. For example, one can take

$$\Omega = \frac{C}{m+1} [f(\boldsymbol{\sigma}) - k_s(\vartheta)]^{m+1}, \quad (97)$$

which yields

$$\mathbf{D}^p = C [f(\boldsymbol{\sigma}) - k_s(\vartheta)]^m \frac{\partial f}{\partial \boldsymbol{\sigma}}. \quad (98)$$

If $f = J_2^{1/2}$, $C = 2/\zeta$, and $k_s(\vartheta) = k^0 = \text{const.}$, Eq. (98) gives

$$\mathbf{D}^p = \frac{1}{\zeta} \left(J_2^{1/2} - k^0 \right)^m \frac{\boldsymbol{\sigma}'}{J_2^{1/2}}, \quad (99)$$

which is a nonlinear Bingham model. If $k_s(\vartheta) = 0$, $f = J_2^{1/2}$, and $C = 2\dot{\gamma}^0/k^m$, Eq. (98) reproduces the power-law J_2 creep given by Eq. (89).

Bibliography

Armstrong P J and Frederick C O 1966 A mathematical representation of the multiaxial Bauschinger effect. *G. E. G. B. Report RD/B/N*, 731.

Asaro R J 1983 Crystal plasticity. *J. Appl. Mech.*, **50**, 921-34.

Budiansky B 1959 A reassessment of deformation theories of plasticity. *J. Appl. Mech.*, **26**, 259-64.

Chen W F and Han D J 1988 *Plasticity for Structural Engineers*. Springer-Verlag, New York.

Christoffersen J and Hutchinson J W 1979 A class of phenomenological corner theories of plasticity. *J. Mech. Phys. Solids*, **27**, 465-87.

Clifton R J 1983 Dynamic plasticity. *J. Appl. Mech.*, **50**, 941-52.

Cristescu N 1967 *Dynamic Plasticity*. North-Holland, Amsterdam.

Dafalias Y F and Popov E P 1975 A model of nonlinearly hardening materials for complex loading. *Acta Mech.*, **21**, 173-92.

DiMaggio F L and Sandler I S 1971 Material model for granular soils. *ASCE J. Engrg. Mech.*, **97**, 935-50.

Drucker D C 1960 Plasticity. *Structural Mechanics – Proc. 1st Symp. Naval Struct. Mechanics*, eds. J N Goodier and N J Hoff, pp. 407–455. Pergamon Press, New York.

Drucker D C and Prager W 1952 Soil mechanics and plastic analysis or limit design. *Q. Appl. Math.*, **10**, 157-65.

Gurson A L 1977 Continuumtheory of ductile rapture by void nucleation and growth – Part I: Yield criteria and flow rules for porous ductile media. *J. Enngng. Mater. Tech.*, **99**, 2–15.

Havner K S 1992 *Finite Plastic Deformation of Crystalline Solids*. Cambridge University Press, Cambridge.

Hecker S S 1976 Experimental studies of yield phenomena in biaxially loaded metals. *Constitutive Equations in Viscoplasticity: Computational and Engineering Aspects, AMD Vol. 20*, eds. J A Stricklin and K J Saczalski, pp. 1–33. ASME, New York.

Hencky H 1924 Zur Theorie plastischer Deformationen und der hierdurch im Material hervorgerufenen Nachspannungen. *Z. angew. Math. Mech.*, **4**, 323-34.

Hill R 1950 *The Mathematical Theory of Plasticity*. Oxford University Press, London.

Hill R 1967 The essential structure of constitutive laws for metal composites and polycrystals. *J. Mech. Phys. Solids*, **15**, 79–95.

Hill R 1978 Aspects of invariance in solid mechanics. *Advances in Applied Mechanics*, **18**, 1–75.

Hill R and Rice J R 1973 Elastic potentials and the structure of inelastic constitutive laws. *SIAM J. Appl. Math.*, **25**, 448-61.

Hutchinson J W 1974 Plastic buckling. *Advances in Applied Mechanics*, **14**, 67–144.

Ilyushin A A 1961 On the postulate of plasticity. *Prikl. Math. Mekh.*, **25**, 503-7.

Ilyushin A A 1963 *Plasticity. Foundations of the General Mathematical Theory*. Izd. Akad. Nauk SSSR, Moscow (in Russian).

Johnson G R and Cook W H 1983 A constitutive model and data for metals subjected to large strains, high strain rates, and high temperatures. *Proceedings of the 7th International Symposium on Ballistics*, pp. 1–7. The Hague, The Netherlands.

Johnson W and Mellor P B 1973 *Engineering Plasticity*. Van Nostrand Reinhold, London.

Johnston W G and Gilman J J 1959 Dislocation velocities, dislocation densities, and plastic flow in LiF crystals. *J. Appl. Phys.*, **30**, 129–44.

Kachanov L M 1971 *Foundations of Theory of Plasticity*. North-Holland, Amsterdam.

Khan A S and Huang S 1995 *Continuum Theory of Plasticity*. John Wiley & Sons, New York.

Koiter W 1953 Stress-strain relations, uniqueness and variational theorems for elastic-plastic materials with a singular yield surface. *Q. Appl. Math.*, **11**, 350-54.

Krieg R D 1975 A practical two surface plasticity theory. *J. Appl. Mech.*, **42**, 641-46.

Lee E H 1969 Elastic-plastic deformation at finite strains. *J. Appl. Mech.*, **36**, 1-6.

Lubarda V A and Krajcinovic D 1995 Some fundamental issues in rate theory of damage-elastoplasticity. *Int. J. Plasticity*, **11**, 763-97.

Lubliner J 1990 *Plasticity Theory*. Macmillan Publishing Comp., New York.

Malvern L E 1951 The propagation of longitudinal waves of plastic deformation in a bar of material exhibiting a strain-rate effect. *J. Appl. Mech.*, **18**, 203-8.

Mear M E and Hutchinson J W 1985 Influence of yield surface curvature on flow localization in dilatant plasticity. *Mech. Materials*, **4**, 395-407.

Mróz Z 1967 On the description of anisotropic work-hardening. *J. Mech. Phys. Solids*, **15**, 163-75.

Naghdi P M 1960 Stress-strain relations in plasticity and thermoplasticity. *Plasticity - Proc. 2nd Symp. Naval Struct. Mechanics*, eds. E H Lee and P Symonds, pp. 121-167. Pergamon Press, New York.

Naghdi P M 1990 A critical review of the state of finite plasticity. *J. Appl. Math. Physics*, **41**, 315-94.

Neale K W 1981 Phenomenological constitutive laws in finite plasticity. *SM Archives*, **6**, 79-128.

Needleman A 1982 Finite elements for finite strain plasticity problems. *Plasticity of Metals at Finite Strain: Theory, Experiment and Computation*, eds. E H Lee and R L Mallett, pp. 387–443. Div. Appl. Mechanics, Stanford University, Stanford.

Nemat-Nasser S 1983 On finite plastic flow of crystalline solids and geomaterials. *J. Appl. Mech.*, **50**, 1114-26.

Nemat-Nasser S 1992 Phenomenological theories of elastoplasticity and strain localization at high strain rates. *Appl. Mech. Rev.*, **45**, S19-45.

Nemat-Nasser S and Shokooh A 1980 On finite plastic flows of compressible materials with internal friction. *Int. J. Solids Struct.*, **16**, 495–514.

Palmer A C, Maier G and Drucker D C 1967 Normality relations and convexity of yield surfaces for unstable materials and structures. *J. Appl. Mech.*, **34**, 464-70.

Perzyna P 1966 Fundamental problems in viscoplasticity. *Advances in Applied Mechanics*, **9**, 243–377.

Phillips A 1982 Combined stress experiments in plasticity – The effects of temperature and time. *Plasticity of Metals at Finite Strain: Theory, Experiment and Computation*, eds. E H Lee and R L Mallett, pp. 230–252. Div. Appl. Mechanics, Stanford University, Stanford.

Prager W 1956 A new method of analyzing stresses and strains in work-hardening plastic solids. *J. Appl. Mech.*, **23**, 493-96.

Prager W 1958 Non-isothermal plastic deformation. *Koninkl. Ned. Acad. Wetenschap. Proc.*, **61**, 176-82.

Rice J R 1970 On the structure of stress-strain relations for time-dependent plastic deformation in metals. *J. Appl. Mech.*, **37**, 728-37.

Rice J R 1971 Inelastic constitutive relations for solids: an internal variable theory and its application to metal plasticity. *J. Mech. Phys. Solids*, **19**, 433-55.

Rice J R 1976 The localization of plastic deformation. *Theoretical and Applied Mechanics*, ed. W T Koiter, pp. 207–220. North-Holland, Amsterdam.

Rudnicki J W and Rice J R 1975 Conditions for the localization of deformation in pressure-sensitive dilatant materials. *J. Mech. Phys. Solids*, **23**, 371-94.

Spitzig W A, Sober R J and Richmond O 1975 Pressure dependence of yielding and associated volume expansion in tempered martensite. *Acta metall.*, **23**, 885-93.

Tvergaard V 1982 On localization in ductile materials containing spherical voids. *Int. J. Fracture*, **18**, 237-52.

Ziegler H 1959 A modification of Prager's hardening rule. *Q. Appl. Math.*, **17**, 55–65.